

TL 5-1064-2024

Issue No.: 2

Uncontrolled printing

Effective from: 11.11.2024

## Waterproofing membrane FATRAFOL 924 P

### PRODUCT DESCRIPTION

FATRAFOL 924 P is a non-reinforced waterproofing roof membrane made on the basis of thermoplastic polyolefins (TPO). The membrane is UV resistant and can be exposed to direct weathering.

### TECHNICAL PARAMETERS

Parameter	Standard	Value for assigned thickness	
		1.80 mm	2.00 mm
Visible defects	EN 1850-2	pass	
Streightness	EN 1848-2	≤ 50 mm	
Flatness	EN 1848-2	≤ 10 mm	
Mass per unit area	EN 1849-2	1.61 kg/m <sup>2</sup>	1.80 kg/m <sup>2</sup>
Water tightness, 60 kPa	EN 1928 met. B	pass	
Reaction to fire	EN 13501-1	class E	
Joint peel resistance	EN 12316-2	≥ 290 N/50 mm	
Joint shear resistance	EN 12317-2	≥ 750/750 N/50 mm	≥ 800/800 N/50 mm
		(or breakege out of joint)	
Tensile strength	EN 12311-2 method B	≥ 16/15 N/mm <sup>2</sup>	
Elongation at break		≥ 550 %	
Impact resistance	EN 12691 method B	≥ 1000 mm	
Resistance to static load	EN 12730 method B	≥ 25 kg	
Tear resistance	EN 12310-2	≥ 150 N	
Tear resistance	EN 12310-1	≥ 550/500 N	≥ 650/600 N
Resistance to root penetration	EN 13948	pass	
Dimensional stability	EN 1107-2	≤ 0.5 %	
Foldability at low temperature	EN 495-5	≤ -40 °C	
Exposure to UV radiation, elevated temperature and water (5000 h)	EN 1297	pass, grade 0	
Water vapour properties - moisture resistance factor μ	EN 1931	280000 ± 30 %	
Heat aging - change in tensile strength - change in elongation at break	EN 12311-2	Δ ≤ 5 %	
Hail resistance	EN 13583	≥ 30 m/s	
Resistance to algae and microorganisms	ISO 846	pass	

MD - Machine Direction, CD - Cross Direction; Mass per unit area tolerance: - 5 % /+10 %

## APPROVALS / CERTIFICATES

- Declaration of performance and CE marking according to EN 13956
- Classification of external fire performance according to EN 13501-5: F<sub>ROOF</sub>

## DIMENSIONS

Thickness [mm] (EN 1849-2)	Width [mm] (EN 1848-2)	Length [m] (EN 1848-2)	Quantity on the roll [m <sup>2</sup> ]*
1.80	2100	20	42.0
2.00	2100	20	42.0

Thickness tolerance: -5 % / +10 %, width tolerance: -0.5 % / +1 %, length tolerance: -0 % / +5 %

\* informative value

## COLOUR AND APPEARANCE

The colour of the top layer is light grey ~ RAL 7035 or white ~ RAL 9016. The colour of the bottom layer is black.

The colour shade of various production batches of the membranes may differ. Minor colour differences are not considered justified grounds for a claim.

## USAGE

FATRAFOL 924 P is intended:

- only as an accessory to FATRAFOL TPO reinforced waterproofing roof membranes
- for detailing of uneven surfaces of the roofs insulated with FATRAFOL TPO
- for patching of expansion joints of FATRANYL TPO coated metal sheets
- for the production of detailed TPO accessories and patches

The membrane is not suitable for an all-over insulation of the entire roof.

## APPLICATION

FATRAFOL 924 P can be laid on roofs only by specialised firms whose workers have been trained properly.

FATRAFOL 924 P is applied in compliance with the principles determined and described in the Construction and Technological Instruction FATRAFOL-S (PN 5415/2011), as amended at the time of the membrane's application, which is available at [www.fatrafol.cz](http://www.fatrafol.cz).

## STORAGE

Store at temperatures between -5 °C and +30 °C. On the site, it is necessary to protect the membrane against pollution. It is recommended to protect the membrane against weather effects until it is applied on the roof.

## MORE INFORMATION

For more information, please see the manufacturer's website [www.fatrafol.cz](http://www.fatrafol.cz).

## LEGAL CLAUSE

The technical data contained herein is based on our current knowledge and experience and relate to the use of the products under normal conditions for application. The information that is included in the current Technical Data Sheet is determined by the method of use and is incomplete. Before using this product, the user is obliged to check whether the product is suitable for the intended use. In addition to that, all users should contact the dealer or manufacturer of this product to obtain additional technical information regarding its use in case they are of the opinion that the information available to them requires some explanation, for both the standard and specific use of this product. Please always make sure that you have the latest version of the product's Technical Data Sheet at your disposal. This Data Sheet and additional information can be obtained from the sales or technical representative of the manufacturer or on the manufacturer's website.

## PRODUCER

Fatra, a. s., třída Tomáše Bati 1541, 763 61 Napajedla, Czech Republic  
tel.: +420 577 50 3325 (1111)  
e-mail: [studio@fatrafol.cz](mailto:studio@fatrafol.cz)  
<http://www.fatrafol.cz>

